



PAGEL®-QUICK SETTING MORTAR

PROPERTIES

- **Quick-setting mortar** for infilling and all types of repairs (Processing time approx. 2 - 5 min.)
- **Extremely easy to use**, only needs to be mixed with water
- Forms a highly plastic and malleable mass that – depending on temperature – can already be loaded within a matter of minutes
- Cement-based, chloride-free, does not bloom or cause iron components to corrode
- Waterproof, largely impermeable to oil and anti-corrosive
- High **early strengths**. PAGEL QUICK SETTING MORTAR achieves a compressive strength of 5 N/mm² (1 h) and 60 N/mm² (28 d) within a very short time.
- An indispensable **installation aid** for all fitters and construction specialists
- Produced and certified in accordance with **ISO 9001**

FIELDS OF APPLICATION

- For **infilling** the areas around anchors, gate mounting parts, railings, tie bars, machine components, steel girders etc.
- For **sealing water leaks**
- For **sealing** and filling in holes and gaps
- For **filling in gaps** around tiles
- For **filling gaps** following all kinds of installation work, such as performed by locksmiths, electricians, brick layers, painters and decorators and fitters
- For sealing the surfaces of cracks filled with special materials and for filling in masonry and concrete cracks

B 1



PAGEL®-QUICK SETTING MORTAR

B 1

TECHNICAL DATA

TYPE				B 1
Compressive strength	1 h	N/mm ²	≥	2.5
	2 h	N/mm ²	≥	5
	24 h	N/mm ²	≥	30
	7 d	N/mm ²	≥	40
	28 d	N/mm ²	≥	65
Mixing water	app. %			20
Mixing time	app. min.			1

All test data are guide values, proofed in our German manufacturing plants, - values from other manufacturing plants may vary.

Storage:: Can be stored for up to 6 months in a sealed container

Packaging: 15-kg bucket

Hazard class: Non-dangerous goods; please read the information provided on the packaging

GISCODE: ZP1

APPLICATION

SUBSURFACE: Clean surface thoroughly and remove all loose objects, cement slurries and any objects that might prevent the mortar from adhering to the surface; wet surface thoroughly.

MIXING: Thoroughly mix the mortar with water at a ratio of: B1 (B2) = 1:2 to 1:3 inside a suitable container. Mixing time: approx. 1 minute.

APPLICATION: B1 PAGEL BLITZMÖRTEL (QUICK SETTING MORTAR) apply immediately after mixing.

Chisel out a dovetail shaped space around difficult areas requiring repairs.

When fixing water leaks, firmly press the mortar plug into the hole and keep pressing into the hole for approx. 3 minutes.

Specialist Company «ASOKA»
Khayrullin Ruslan
E-mail: mail@superbeton.su
Russia - Moscow, Frunzenskaya nab. 30,
28 office.
Phone: (495) 648-52-04
Fax: (495) 781-60-70
Cell phone: 8-926-535-39-36
Internet: www.superbeton.su

All of the information, technical advice and recommendations provided in this brochure are based on comprehensive research and practical experience. However, they are - including with regard to third-party property rights - for information only and do not release customers from their responsibility to check whether the above products and procedures are suitable for their intended use. The above test data has been derived under standard climatic conditions and in accordance with DIN 50014. These values are average values and analyses, and product values may slightly differ upon delivery. Any recommendations contrary to those stated in this brochure require our written consent. The planner and processing company must always obtain information on the latest state of the art and relevant valid edition of this brochure. Please do not hesitate to contact our customer service department at any time and many thanks you for your interest. This brochure makes all previously published product information null and void. Please visit our website for the latest valid version of this brochure at www.pagel.com.



PAGEL®
SPEZIAL-BETON GMBH & CO. KG

WOLFSBANKRING 9 · D-45355 ESSEN
TEL. +49 (0) 2 01-6 85 04-0 · FAX +49 (0) 2 01-6 85 04-31
INTERNET: WWW.PAGEL.COM · E-MAIL: INFO@PAGEL.COM